

RUST-OLEUM®
INDUSTRIAL



NS200/300/500

Anti-slip additives for 2K paints



- Durable aluminium oxide anti-slip additive
- Resists vehicular traffic
- Choice of 3 different granule sizes
- Can be pre-mixed or broadcasted over wet paint
- For any 2K paint

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

NS200/300/500

DESCRIPTION

Anti-slip granulates, made of thermally split flint stones, turn a standard floor coating into a durable anti-slip coating.

RECOMMENDED USE

Non-Skid 200, 300 & 500 Additives are intended to be added to floor coatings to produce a non-skid surface. Anti-slip additives can be used in combination with the following RUST-OLEUM 2K-Floor coatings: 5500; 9100, Pegakote, 5800, 9700 and Rust-O-Thane® Polyurethane Topcoats. Non-Skid Additives can be mixed with the required RUST-OLEUM coating system or can be sprinkled into the freshly applied coating manually or with special low pressure spraying equipment. Intended for Non-Skid industrial flooring and should be topcoated with the required RUST-OLEUM System if sprinkled.

TECHNICAL DATA

Density: 2.3 kg/l
Solids content in volume: 100%
Solids Content in weight: 100%

DRYING TIMES AT 20°C/RH 50%

THEORETICAL CONSUMPTION

NS200/300: Sparingly: 20 m²/kg (= 200 g/l if mixed in), Dense: 10 m²/kg (= 400 g/l if mixed in)

NS500: Sparingly: 5 m²/kg, Dense: 2 m²/kg.

PRACTICAL CONSUMPTION

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

DIRECTIONS FOR USE

Sprinkling: sprinkle the granulates onto the freshly applied, wet RUST-OLEUM coating, manually with a "sprinkler-box" for small areas, or with special low-pressure spraying equipment with a nozzle opening of at least 18 mm ; air pressure between 1 - 3 bars.

Mixing: mix the granulates into the wet coating material and apply the coating with a roller or a brush (not by spraying), stir regularly to avoid settling of the granulates.

APPLICATION CONDITIONS

For optimum results, follow the application conditions with the applied RUST-OLEUM Floor Coating.

REMARKS

For coating systems with a dry film thickness less than 300 µm it is recommended to use NS 200. For 1K-paints, use NS100.

Particle size: NS200: 0.2 - 0.5 mm, NS300: 0.5 - 1.0 mm, NS500: 0.8 - 1.5 mm. NS500 is available in white (aluminium oxide) and black (carborundum/iron oxide) - use white for light coating colours and black for darker coating colours.

SAFETY DATA

SHELF LIFE

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 19/10/2016

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Postbus 138
4700 AC Roosendaal
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Rust-Oleum UK Ltd.
PO Box 261
Chester-le-Street
DH3 9EH United Kingdom
T : +44 (0)2476 717 329
F : +44 (0)2476 718 930
info@rust-oleum.eu

Rust-Oleum France S.A.S.
11, rue Jules Verne - B.P. 60039
95322 St-Leu-La-Forêt Cedex
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu