

RUST-OLEUM®
— INDUSTRIAL —



EPOXYSHIELD® SEALER



Water based, cost effective dust-proofer

- Single pack, easy to apply
- Non yellowing clear finish (gloss)
- Touch dry after just 1 hour
- Ideal primer for EpoxyShield® ULTRA coatings

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

EPOXYSHIELD® SEALER

DESCRIPTION

One component, water-based, concrete sealer based on a vinyl acrylic binder. It reduces dust production and simplifies cleaning.

RECOMMENDED USE

When EpoxyShield® Sealer is used as a finish, apply 2 coats. EpoxyShield® Sealer can also be used as a sealer/impregnation primer for EpoxyShield® 5200 ULTRA. Apply the sealer on bare and clean concrete floors.

TECHNICAL DATA

Density:	1,02
Gloss Level:	Gloss
Solids content in volume:	30%

DRYING TIMES AT 20°C/RH 50%

Touch dry: approximately 1 hour

THEORETICAL CONSUMPTION

Maximum 10 m² per litre.

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Apply the product only on fully clean and dry concrete surfaces. Do not apply on smooth or very dense concrete or concrete which contains curing compound. Remove all oil, grease and other dirt using EpoxyShield® Cleaner/Degreaser 2901. New concrete has to cure for minimal 30 days. All laitance, loose or unsound concrete should preferably be removed by blasting, cutting or etching with RUST-OLEUM Surfa-Etch 108 Etching Solution. Repair all holes and cracks with EpoxyShield® concrete repair products. Very dense and smooth concrete should first be abrasive blasted (or etching). During application the substrate should be clean and dry.

DIRECTIONS FOR USE

Mix the product prior for use.

APPLICATION CONDITIONS

Temperature of air, substrate and coating material between 10 and 35°C, relative humidity below 85%. The substrate temperature must be at least 3°C above dew point. Ventilate well during and after application.

APPLICATION & THINNING: BRUSH

Product is ready for use. Thinning is not necessary.

APPLICATION & THINNING: ROLLER

Product is ready for use. Thinning is not necessary.

CLEANING OF EQUIPMENT / SPILLS

Direct after application with water and soap.

REMARKS

Walkable: after 8 - 12 hours

SAFETY DATA

VOC level:	77 g/l
VOC ready mix:	77 g/l
VOC category:	A/i
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 25/04/2019

Available colours & pack sizes : Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer : The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu